

# DuPont™ Cyrel® DEC

## The Robust All-Purpose Plate for the Corrugated Market



DuPont™ Cyrel® DEC

[DuPont Packaging Graphics](#) continues to be a global technology leader in the development and supply of flexographic printing systems. Our R&D team continues to develop innovative new solutions to help our customers expand their business by taking advantage of new and profitable opportunities in the growing flexographic packaging market. The DuPont Packaging Graphics portfolio of products includes DuPont™ Cyrel® brand photopolymer plates ([analogue](#) and [digital](#)), [Cyrel® platemaking equipment](#), [Cyrel® round sleeves](#), Cyrel® plate mounting systems and the revolutionary [Cyrel® FAST thermal system](#).

DuPont™ Cyrel® Systems: Higher quality at high speed.

**DuPont™ Cyrel® DEC is a soft digital plate for corrugated board applications withstanding even demanding requirements.**

### DuPont™ Cyrel® DEC

#### Applications

- Corrugated post-print
- Sacks
- Rough paper surfaces

#### Product Features

- Excellent ink transfer permits superior printing uniformity
- High exposure resolution results in better quality reproduction
- Image relief is clean and sharp
- Exceptional exposure latitude allows single exposure without masking
- Excellent thickness uniformity
- Less make ready time
- High resistance to ozone and white light results in excellent storage capability

#### Printing Ink and Solvent Compatibility

Cyrel® DEC offers excellent compatibility with water-based inks.

#### Process of Use

Expose the plate through the back to establish the floor and maximize sensitivity. Back exposure varies according to relief required. Remove the protective coversheet and image the plate with a Cyrel® Digital Imager (CDI). Expose the front of the plate surface. Process the plate in a Cyrel® solvent processor to remove unexposed polymer. Finish the plate in a light finisher to eliminate surface tackiness.

#### Mounting

Cyrel® DEC is perfectly fit to be mounted either on a polyester mounting film or in combination with a compressible foam, especially Cyrel® CyCOMP.



Download latest version

# DuPont™ Cyrel® DEC

## The Robust All-Purpose Plate for the Corrugated Market

### Handling – Raw Material

Cyrel® DEC plates should be handled under UV free light; e.g. fluorescent tubes covered with amber sleeves.

### Storage – Finished Plates

After printing, plates should be thoroughly cleaned with a compatible solvent before storing. They may be stored on cylinders, sleeves or demounted and stored flat.

For more information on DuPont™ Cyrel® or other DuPont Packaging Graphics products, please contact your local representative:

#### DuPont de Nemours (Deutschland) GmbH

DuPont Electronics & Communications  
Hugenottenallee 175  
63263 Neu-Isenburg  
Germany  
Tel.: +49 (0) 6102 18 1592

#### DuPont (U.K.) Limited

DuPont Electronics & Communications  
Wedgwood Way, Stevenage  
Hertfordshire SG1 4QN  
United Kingdom  
Tel: +44 (0) 1438 73 4863

[www.cyrel.eu](http://www.cyrel.eu)

Technical Data	Cyrel® DEC 112 Thickness 2.84 mm / 0.112 inch	Cyrel® DEC 125 Thickness 3.18 mm / 0.125 inch	Cyrel® DEC 155 Thickness 3.94 mm / 0.155 inch	Cyrel® DEC 170 Thickness 4.32 mm / 0.170 inch	Cyrel® DEC 185 Thickness 4.70 mm / 0.185 inch
<b>Durometer</b>	38 Sh A	37 Sh A	36 Sh A	36 Sh A	36 Sh A
<b>Image Reproduction</b>	3-95% / 42 L/cm	3-95% / 42 L/cm	3-95% / 36 L/cm	3-95% / 28 L/cm	3-95% / 28 L/cm
<b>Minimum Positive Line Width</b>	7 mil / 0.175 mm	7 mil / 0.175 mm	12 mil / 0.300 mm	12 mil / 0.300 mm	14 mil / 0.350 mm
<b>Minimum Isolated Dot</b>	500 µm	500 µm	500 µm	500 µm	500 µm
<b>Relief Depth</b>	1.00-1.20 mm / 0.039-0.047 inch	1.00-1.20 mm / 0.039-0.047 inch	1.50-2.00 mm / 0.059-0.079 inch	1.50-2.00 mm / 0.059-0.079 inch	Max 2.50 mm / 0.098 inch
	<b>Cyrel® DEC 197 Thickness 5.00 mm / 0.197 inch</b>	<b>Cyrel® DEC 217 Thickness 5.51 mm / 0.217 inch</b>	<b>Cyrel® DEC 237 Thickness 6.02 mm / 0.237 inch</b>	<b>Cyrel® DEC 250 Thickness 6.35 mm / 0.250 inch</b>	
<b>Durometer</b>	36 Sh A	36 Sh A	36 Sh A	36 Sh A	
<b>Image Reproduction</b>	3-95% / 28 L/cm	3-95% / 28 L/cm	3-95% / 28 L/cm	3-95% / 28 L/cm	
<b>Minimum Positive Line Width</b>	14 mil / 0.350 mm	14 mil / 0.350 mm	14 mil / 0.350 mm	14 mil / 0.350 mm	
<b>Minimum Isolated Dot</b>	500 µm	500 µm	500 µm	500 µm	
<b>Relief Depth</b>	Max 2.50 mm / 0.098 inch	Max 2.50 mm / 0.098 inch	Max 2.50 mm / 0.098 inch	Max 2.50 mm / 0.098 inch	