

# DuPont™ Cyrel® DFUV

## Highest Print Quality with UV Inks



DuPont™ Cyrel® DFUV

[Preliminary Technical Data Sheet](#)

[DuPont Packaging Graphics](#) continues to be a global technology leader in the development and supply of flexographic printing systems. Our R&D team continues to develop innovative new solutions to help our customers expand their business by taking advantage of new and profitable opportunities in the growing flexographic packaging market. The DuPont Packaging Graphics portfolio of products includes DuPont™ Cyrel® brand photopolymer plates ([analogue](#) and [digital](#)), Cyrel® platemaking equipment, Cyrel® round sleeves, [Cyrel® plate mounting systems](#) and the revolutionary [Cyrel® FAST thermal system](#).

DuPont™ Cyrel® Systems: Higher quality at high speed.

**Cyrel® FAST DFUV is a thermal process plate for use with UV inks that comes to colour quickly and prints smooth and dense solids, without compromising dot gain, highlights and resolution. DFUV is specifically designed for shorter, narrow web print runs using UV inks on high priced stock, where minimizing the startup waste is essential. Cyrel® DFUV comes up to colour almost immediately and is designed for very fine screens.**

### DuPont™ Cyrel® DFUV

#### Applications

High-end substrates including:

- Pressure sensitive labels
- Self-adhesive labels
- Shrink wrap labels
- Wrap around labels
- Tickets/tags/boards

#### Product Features

- Comes up to colour very quickly and predictably for reduced setup time and reduced material waste
- Extremely rapid access time thanks to thermal plate processing where no drying step is needed
- High and uniform/smooth UV ink transfer for outstanding tonal reproduction
- Very high resolution capability enabling > 200 lpi screens
- Excellent for printed security features and micro text down 1 pt
- High durability on press

- Exceptional thickness uniformity with no plate swelling during platemaking
- High resistance to ozone and white light results in excellent storage capability

#### Printing Ink and Solvent Compatibility

Cyrel® DFUV is specifically designed for use with UV inks due to its excellent compatibility and resistance. Also offers comparable compatibility with solvent-based, and water-based inks.

#### Platemaking

The Cyrel® FAST thermal developer allows the production of Cyrel® FAST finished plates in less than one hour, making it the ideal just-in-time platemaking system for a market that demands quick turnaround at the highest possible quality. The Cyrel® FAST thermal developer delivers outstanding plate quality and uniformity. This processor has the ability to produce a finished plate without solvent washout. The Cyrel® ECLF for exposing and light finishing plates is available to complement the Cyrel® FAST thermal developer.



Play Video



Download latest version

# DuPont™ Cyrel® DFUV

## Highest Print Quality with UV Inks

### Process of Use

DuPont™ Cyrel® DFUV is designed to work with Cyrel® FAST thermal platemaking. Expose the plate through the back to establish the floor and minimize sensitivity. Back exposure varies according to relief required. Remove the protective coversheet, and image the plate with a Cyrel® Digital Imager (CDI). Expose the front of the plate surface. Process the plate in the Cyrel® FAST thermal developer. Finish the plate in a light finisher to eliminate surface tackiness. Post-expose the plate to ensure complete polymerization.

### Mounting

Cyrel® Microflex mounting devices are recommended for mounting Cyrel® DFUV plates. The double sided adhesive should first be applied to the cylinder or sleeve – not the plate – to ensure easier and precise laydown. The polyester base will maintain accurate register even with large plates.

### Storage – Raw Material

Store unexposed plates in a cool area (4–32°C, 40–90°F), away from direct sources of heat. Humidity control is not required. Cyrel® DFUV is foam interleaved to provide maximum protection of the plate after manufacture, and during transportation and storage. Plates should be stacked flat. Plates should not be exposed to direct sunlight or excessive white light. Continuous exposure to very high ozone concentrations should be avoided.

### Handling – Raw Material

Like all photopolymer plates, Cyrel® DFUV plates should be handled under UV free light; e.g. fluorescent tubes covered with amber sleeves.

### Storage – Finished Plates

After printing, plates should be thoroughly cleaned with a compatible solvent before storing. They may be stored on cylinders, sleeves or demounted and stored flat.

Technical Data		
	Cyrel® DFUV 45 Thickness 1.14 mm / 0.045"	Cyrel® DFUV 67 Thickness 1.70 mm / 0.067"
<b>Durometer</b>	76 Sh A	73 Sh A
<b>Image Reproduction</b>	1–98% / 80 L/cm/200 lpi	1–98% / 80 L/cm/200 lpi
<b>Minimum Positive Line Width</b>	0.100 mm / 4 mil	0.100 mm / 4 mil
<b>Minimum Isolated Dot Size</b>	200 µm	200 µm
<b>Relief Depth</b>	max. 0.55 mm / max. 0.022"	max. 0.65 mm / max. 0.026"

For more information on DuPont™ Cyrel® or other DuPont Packaging Graphics products, please contact your local representative:

[www.cyrel.com/ap](http://www.cyrel.com/ap)

DuPont China Holding Co., LTD  
Bldg 11, 399 Keyuan Road  
Zhangjiang, Hi-Tech Park  
Pudong New District  
Shanghai 201203 China  
Tel: (86) 21 3862 2888

DuPont Malaysia SDN BHD  
1st Floor, Bangunan Samundra  
No. 1, Jalan Kontraktor  
U1/14 Seksyen U1  
Hicom-Glenmarie, Industrial Park  
40150 Shah Alam, Selangor Darul Ehsan  
Malaysia  
Tel: (60) 3 5569 3006

DuPont K.K. - Japan  
Sanno Park Tower  
11-1, Nagata-cho 2-chrome  
Chiyoda-ku, Tokyo 100-6111, Japan  
Tel: (81) 3 5521 8520

DuPont Australia, LTD  
Level 1, 600 Victoria St.  
Richmond, Victoria 3121, Australia  
Tel: (61) 3 9935 5699

E.I. DuPont India Private Limited  
1001-10012, 'Meadows', 10th Floor  
Sahar-Plaza Complex, Andheri-Kurla Road  
Andheri (East), Mumbai 400 059  
Tel: (91) 22 6751 5000